

3C Sealants®







Product Technical Data Sheet

Product Name: 3C Sealants Smooth Finish 2 in 1



DESCRIPTION:

A premium quality, super fast curing, 2 in 1 epoxy resin filler for fine surface repairs on wood, stone and metal. The convenient single cartridge design allows for easy extrusion from a standard sealant skeleton gun.

INSTRUCTIONS OF USE:

Each unit contains component A & B, in one easy to use cartridge, with a 1:1 mix ratio. Mix material well until evenly coloured (Light Beige). Pot life: 6-8 minutes after mixing (20°C).

BENEFITS:

- Overpaintable within 1 hour
- Solvent-free / very low odour
- Non-slump on verticle & overhead applications
- Can be easily sanded & shaped
- Fantastic adhesion to wood, metal & stone
- Fast, simple mixing with 1:1 ratio
- For internal and external use
- For quick repairs up to 10mm
- Use with a standard sealant skeleton gun

PRODUCT INFORMATION

Packaging	250ml cartridge
Shelf Life	12 months
Colour	Beige
Storage	Store unopened cartridge in cool dry conditions +5°C to +25°C
Pot life (20°C)	6-8 mins
Mix ratio	1:1 in volume
Skin Formation Time	15 minutes
Overpaintable/Sandable	Approx. 1 hour
Specific gravity Part A	1.50 kg/l (± 0.03)
Specific gravity Part B	1.52 kg/l (± 0.03)

DESIGNED FOR:

Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. Toxic to aquatic life with long lasting effects. Avoid breathing dust/fume/gas/mist/vapours/spray. Avoid release to the environment. Wear protective gloves/clothing and eye/face protection. If skin irritation or rash occurs: Get medical advice/attention. If eye irritation persists: Get medical advice/attention. Contains epoxy constituents. May produce an allergic reaction. Contains: 2-Propenoic acid, reaction products with dipentaerythritol bis-[4-(2,3-epoxipropoxi) phenyl]propane Formaldehyde, oligomeric reaction products with 1-chloro-2,3-epoxypropane and phenol oxirane, mono[(C12-14-alkyloxy)methyl] derivs. 2-Propenoic acid, reaction products with pentaerythritol.



This technical data sheet replaces all previous editions. The data on this sheet have been complied according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for their application. Therefore, tests are necessary. Our general conditions apply.