

# **ARBO PRIMER 2650**

ARBO <sup>®</sup> 2650 Primer is a one-part, solvent containing, air-drying polyacrylate/silane blend-based primer.

### **Main Applications**

Recommended for use in conjunction with the Arbosil and Arbomeric products for the priming of porous surfaces such as concrete, blockwork, brickwork etc.

#### **Application Instructions**

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate ARBO Cleaner. Apply one coat of ARBO 2650 Primer using a clean dry brush and allow it to dry for at least 1 hour but not more than 8 hours before applying the sealant. Strictly adhere to user Instructions shown on the tin.

Consult ARBO Technical Services for advice regarding primer in specific instances.

All joint preparation and priming should be carried out in accordance with BS 8000 -16,: 1997 + A1: 2010 the British Standard for the sealing of joints in buildings using sealants.





## **ARBO PRIMER 2650**

### Storage Life

6 months in original unopened package stored in a cool, dry place out of direct sunlight.

### **Health and Safety**

For full information please refer to the Safety Data Sheet.

### **Packaging**

ARBO 2650 Primer is supplied in 500ml containers (yield approximately 125 metres per 500ml).

Technical Data	
Colours:	Colourless
Density	Approx 0.95 g/cm <sup>3</sup>
Application Temperature:	+ 5° C to + 30° C
Cleaning:	Tools must be carefully cleaned immediately after use with an appropriate cleaner.

Important: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. It is the user and specifier's responsibility to ensure ARBO product is suitable for the intended use: consult ARBO Technical Services for specific advice. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.



