

1-component silicone sealant based on aminoxime MEKO-free

For indoor and outdoor application

Characteristic:

- **Wide range of colours**
Colour adapted to common floor coverings (e.g. PVC, rubber and linoleum)
- **Flame retardant - building material class B1 according to DIN 4102 and DIN EN ISO 4589**
For special fire protection requirements
- **Excellent weathering, ageing and UV-resistance**
For long-lasting indoor and outdoor applications

Fields of application:

- Floor and connection joints for plastic and design floor coverings made of rubber, linoleum, vinyl and PVC
- Equalizing sealing of similar and dissimilar working materials such as glass, stainless steel, aluminium and some plastics

Standards and tests:

- Tested according to EN 15651 – Part 1: F EXT-INT CC 25 LM
- Tested according to EN 15651 – Part 4: PW EXT-INT CC 25 LM
- Tested according to DIN 4102-B1 – hardly inflammable between solid mineral building materials (wood research at the Munich Technical University)
- Tested according to DIN EN ISO 4589-2:1999 Plastics - Definition of the fire-behaviour due to the oxygen index (Bodycote Warringtonfire)
- Tested for applications in the cleanroom sector by the Institute for Hygiene Gelsenkirchen, Germany
- Classification according to building certification systems, see the sustainability data sheet
- Suitable for applications according to IVD instruction sheet no. 1+11+31+35 (IVD = German industry association sealants)
- French VOC-emission class A+

Important information:

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material.

During curing small amounts of an amine-/oxime-compound are released.

Ensure good ventilation during application and curing.

The required vulcanization time prolongs with increasing thickness of the silicone layer. One-component silicones are not suitable for full-area bonding, unless there are specific structural conditions that require such full-area application. If one-component silicones are to be used for thickness layers of more than 15 mm please contact our technical department beforehand.

For sealing of linoleum floorings please wet smoothing tool with only a little smoothing agent or rebate dryly. Remove excess smoothing agent on the flooring before drying in order to avoid staining.

Avoid contact with materials which contain bitumen and which release solvents, e. g. butyl, EPDM, neoprene, insulating- and bituminous paint.

Indoors without daylight or in the case of sporadic artificial lighting, alkoxy/oxime/amine silicone sealants may exhibit a yellowing over time, especially in transparent and light colours. If technically possible, it is recommended to use acetate silicones in these cases.

Technical properties:

Skin-forming time at 23 °C/50 % RH [minutes]	~ 6
Curing in 24 hours at 23 °C/50 % RH [mm]	~ 2 - 3
Processing temperature from/to [°C]	+ 5 / + 35
Viscosity at 23 °C	pasty, stable
Density at 23 °C according to ISO 1183-1 [g/cm³]	~ 1,3
Shore-A-hardness according to ISO 868	~ 27
Permissible movement capability [%]	25
Stress expansion modulus at 100 % according to ISO 37, type 3 [N/mm²]	~ 0,5
Tensile expansion according to ISO 37, type 3 [%]	~ 550
Tensile strength according to ISO 37, type 3 [N/mm²]	~ 1,2
Temperature resistance from/to [°C]	- 40 / + 150
Shelf life at 23 °C/50 % RH for cartridge/foil bag [months]	18

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Pretreatment:

The adherent surfaces have to be clean, free from fat, dry and sustainable. All adherent surfaces must be clean and any contaminant such as release agents, preserving agents, grease, oil, dust, water, old adhesives or sealants and other substances which could affect adhesion, should be removed. Cleaning of non-porous substrates: Apply OTTO Cleaner T (airing time approx. 1 minute) using a clean, lint-free cotton cloth. Cleaning porous substrates: Clean surfaces with steel-wire brush e. g. or a grinding disk to remove loose particles.

Primer Table:

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer according to the recommendations of our technical department (e. g. +/OTTO Primer 1216) in order to achieve a resilient bonding.

Aluminium	+
Aluminium anodized	+
Aluminium powder-coated	1101 / T
Concrete	1105 / 1215
Floor covering, rubber	+
Floor covering, PVC	+
Floor covering, vinyl	+
Epoxid resin coating	+
Epoxid resin mortar	+ / 1216
Stainless steel	1216
Glass	+
Ceramic, glazed	+
Ceramics, unglazed	+
Linoleum	+
Natural stone / marble	-
Plaster	1105 / 1215
PVC soft	+

+ = good adherence without primer
 - = not suitable
 T = Test/pilot test advised

Application information:

Amin cross-linking silicone sealants may cause yellowing of certain alkyd paints and various plastics or similar - therefore we recommend carrying out trials before use. Due to the many possible influences during and after application, the customer always has to carry out trials first.



Please observe the recommended shelf life which is printed on the packaging.
 We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminution of durability or a change of material characteristics may arise.

Packaging:

	310 ml cartridge
agate grey	S51-04-C62
anthracite	S51-04-C67
aqua	S51-04-C1042
bahamabeige	S51-04-C10
black	S51-04-C04
blue grey	S51-04-C1671
brilliant blue	S51-04-C958
brown	S51-04-C05
brown-red	S51-04-C1063
cherry	S51-04-C17
clay	S51-04-C1053
cloud grey	S51-04-C1670
cream beige	S51-04-C1043
cream-white	S51-04-C7148
crema	S51-04-C1657
dark brown	S51-04-C49
deep sea blue	S51-04-C983
doussie, pear tree	S51-04-C85
dove grey	S51-04-C964
fair oak	S51-04-C64
flash grey	S51-04-C787
lime green	S51-04-C7699
melon	S51-04-C1044
orangina	S51-04-C1129
oxide-red	S51-04-C1131
pale brown	S51-04-C1062
pastel blue	S51-04-C982
pastel green	S51-04-C1008
pastel yellow	S51-04-C1056
patina green	S51-04-C1112
pearl-grey	S51-04-C1662
pine	S51-04-C5128
pure white	S51-04-C1646
rustic oak	S51-04-C98
saffron yellow	S51-04-C1049
sahara	S51-04-C103
sandstone grey	S51-04-C979
signal white	S51-04-C1651
stone grey	S51-04-C79
taupe	S51-04-C1667
thistle-grey	S51-04-C81
titan grey	S51-04-C1172
tomato	S51-04-C1066
transparent	S51-04-C00
violet	S51-04-C1116
white	S51-04-C01
Packaging unit	20
Pieces per pallet	1200

Safety precautions:

Please observe the material safety data sheet.
 After curing the product is completely odourless.

Disposal:

Information about disposal: Please refer to the material safety data sheet.

Warranty information:

All information in this publication is based on our current technical knowledge and experience. However, since conditions and methods of use and application of our products are beyond our control, we suggest that you test the product before final use. Information given in this technical data sheet and explanations of OTTO-CHEMIE in connection with this technical data sheet (e.g. service description, reference to DIN regulations etc.) is not to be seen as a warranty. Warranties require a separate written declaration of OTTO-CHEMIE to prove their validity. The characteristics stated in this data sheet define the characteristics of the article broadly and conclusively. Suggestions of use are not to be taken as confirmation of the appropriateness for the recommended intended use. We reserve the right to alter the product, adjusting it according to technical progress and new developments. We are at your disposal both for inquiries as well as specific application problems. If a governmental approval or clearance is necessary for the application of our products, the user is responsible for the obtainment of such. Our recommendations do not excuse the user from the obligation to take into consideration the possibility of infringement of third parties' rights and - if necessary - resolving it. For the rest our general terms and conditions apply, in particular regarding a possible liability for defects. You can find our general terms and conditions on our homepage: <http://www.otto-chemie.de/en/terms-and-conditions>